

**TECHNICAL FEATURES**

<b>Trade Name</b>	Hot grip
<b>Use</b>	It provides protection against hot containers up to + 260°C and cold containers down to - 57° C
<b>Material</b>	Sylicon rubber
<b>Other features</b>	Internal relief surface

**GENERAL FEATURES**

<b>CE Mark</b>	No
<b>Temperature</b>	+ 260° C – 57°C

**STERILIZATION**

<b>Autoclavability + 121°C</b>	No
<b>Gas (Ethylene Oxide)</b>	Yes
<b>Dry Heat (+160°C)</b>	Yes
<b>Chemical (Formalin)</b>	Yes
<b>Irradiation</b>	No
<b>Microwave</b>	Yes

**CLEANING OPERATIONS**

<b>Slight contamination</b>	Wash with neutral detergent (pH 7)
<b>Consistent contamination</b>	Wash with alkanin detergent (pH up to 12)

**Quality Assurance**  
Massimiliano Capitano

**CHEMICAL RESISTANCES**

Categories of substances	Reference	Concen. %	T. 20°	T. 40°	T. ° 60
Inorganic acid	Sulphuric acid	98	C	-	-
Organic acid	Benzoic acid	100	B	B	C
Alcohol	Ethanol	100	B	B	C
Aldehydes	Acetaldehyde	100	C	-	-
Inorganic alkali	Sodium hydroxide	50	A	B	C
Organic alkali	Aniline	100	C	-	-
Ketone	Acetone	100	C	-	-
Esther	Ethyl acetate	100	C	-	-
Hydrocarbons, halogenated	Dichloroethylene	100	C	-	-
Hydrocarbons, aromatic	Benzene	100	C	-	-
Hydrocarbons, linear	Hexane	100	C	-	-
Supersolvent	Tetrahydrofuran	100	C	-	-

**Legenda** (not applicable if neglected):

- **A: fair resistance**; exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance**; exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance**; exposure to chemical is not allowed, or causes immediate permanent damage.

**Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.**

**PACKAGING**

Bag	1 pc
-----	------

**Quality Assurance**  
Massimiliano Capitano