

TECHNICAL SPECIFICATIONS

| | |
|------------|----------------|
| Trade name | Hoses selector |
| Use | selector |
| Material | ABS green |

DIMENSIONAL SPECIFICATIONS

| | |
|-------------------------------|-------------------------|
| Dimensions | mm. 12,00 x 93 x 166,50 |
| General dimensional tolerance | mm. +/- 1,00 |

GENERAL FEATURES

| | |
|-----------------------|----------------|
| CE mark | No |
| Autoclavability | Yes |
| Sterilization | By irradiation |
| Food contact suitable | Yes |

CHEMICAL RESISTANCE

| Categories of substances | Reference | Concen. % | T. 20° | T. 40° | T.° 60 |
|---------------------------|------------------|-----------|--------|--------|--------|
| Inorganic acid | Sulphuric acid | 98 | C | - | - |
| Organic acid | Benzoic acid | 100 | B | B | B |
| Alcohol | Ethanol | 100 | B | C | - |
| Aldehydes | Acetaldehyde | 100 | B | B | C |
| Inorganic alkali | Sodium hydroxide | 50 | A | A | A |
| Organic alkali | Aniline | 100 | C | - | - |
| Ketone | Acetone | 100 | B | B | C |
| Esther | Ethyl acetate | 100 | C | - | - |
| Hydrocarbons, halogenated | Dichloroethylene | 100 | C | - | - |
| Hydrocarbons, aromatic | Benzene | 100 | C | - | - |
| Hydrocarbons, linear | Hexane | 100 | C | - | - |
| Supersolvent | Tetrahydrofuran | 100 | C | - | - |

Legenda (not applicable if neglected):

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed, or causes immediate permanent damage.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing..

PACKAGING

| | |
|------|--------|
| Box | Pz. 1 |
| Case | Pz. 55 |

Quality Assurance

Massimiliano Capitanio

Technical Direction

Guido Borona